

DISTITRON® 278

First Emission: 09/01/2012

Version: 02, 01/09/2016

Product type

Unsaturated polyester resin in styrene, Orthophthalic-Neopentyllic

Appearance

Yellow - Transparent

Main resin characteristics

High reactivity, Clear, unaccelerated

Main applications

BMC and SMC manufacture, good superficial appearance

Moulding informations

Hot press moulding

Shelf life and storage

Store in the shade, out of direct sunlight. Keep storage temperature below 25°C. Unseal container just before use. Shelf-life will be reduced reaching higher temperature.

Precaution for handling

Read carefully the Safety Data Sheet

Note

FEATURES OF THE LIQUID RESIN

<i>Properties</i>	<i>Test Method</i>	<i>Unit</i>	<i>Typical values</i>
Specific weight at 20°C		g/cm ³	1,11
Brookfield viscosity at 25°C, sp 3 rpm 20	MT-CU025V	mPa.s	2000 - 2200
Solid content	MT-CU001C	%	63 - 65
Reactivity	at 130°C + 1% TBPEH		
Curing time	RS.03.G	seconds	100 - 125
Exothermic peak	RS.03.G	°C	200 - 230
Acidity	MT-CU001I	mgKOH/g	13 - 18
Shelf life at 23°C in the dark	MT-CU002S	months	6

PROPERTIES OF THE CURED UNREINFORCED RESIN

Curing cycle	16h at 70°C + 2h at 100°C + 1h at 100°C		
Tensile strength	ISO 527 (2012)	MPa	45
Tensile modulus	ISO 527 (2012)	MPa	3400
Elongation at break	ISO 527 (2012)	%	1,6
Flexural strength	ISO 178/B (2010)	MPa	100
Flexural modulus	ISO 178/B (2010)	MPa	3300
HDT	ISO 75 -2A (2013)	°C	120
Glass transition	ASTM E 1545 (2011)	°C	125
Barcol hardness at 25°C	ASTM D 2583 (2007)	units	47

The information contained in this document (which is to be intended only for explanatory purposes) is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of publication. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing in the information contained in this document shall be deemed to be a warranty or a representation (explicit or implicit) by the manufacturer, and/or taken or construed as infringing of any existing patents. The manufacturer shall not be under any liability or responsibility for any of the information provided under this document or for any errors, omissions or misstatements, even with regard to results to be obtained through the use of the aforesaid information.