

Technical data sheet

Methyltetrahydrophthalic anhydride/700 K3 (MTHPA/700 K3)

Version: February 2007


Synonyms

1,3-iso-Benzofurandione, tetrahydromethyl

Formula

$C_9H_{10}O_3$

Structural formula



CAS number

11070-44-3

EINECS number

234-290-7

Product specification

Characteristics	Unit	Value	Method*	Reference
Appearance		Clear liquid	L000	
Anhydride equivalent		160 ÷ 165	L001	
Colour	Gardner	7 max	GM011	ASTM D -1544
Viscosity @ 25°C	mPa.s	220 max	G006	DIN 53015
Gel time @ 100°C	min	10 ÷ 13	L032	DIN 16945/16916

* Internal methods available upon request.

Typical properties

Characteristics	Unit	Value
Density @ 25°C	g/ml	1.207
Vapour pressure @ 120°C	mmHg	5.0
Refractive index n_D^{25}		1.5030

Main applications

MTHPA/700 K3 is mainly used as a curing agent for epoxy resins. It has a low tendency to absorb moisture from the air and zero or minimal formation of carbon dioxide when mixed with tertiary amine accelerators.

MTHPA can be easily blended with various liquid resins providing stable, low viscous mixtures and long pot lives. It is widely used for:

- Casting / Potting
- Impregnation
- Lamination

In the field of reinforced plastics it is used for filament winding products (pipes for oil, poles and sport goods), laminated sheets, printed circuit boards, switch gears.

Thanks to its excellent insulating properties, MTHPA found a lot of applications for the production of electrical parts such as: capacitors, resistors, wiring parts transformers, ignition coils, fly back transformers.

Handling

Packaging: galvanized drum 220 kg;
 bulk;
 upon request other form of packaging can be available.

Storage: it must be stored away from open flames or other potential ignition sources, and should be protected from moisture because, especially PI and 600 versions, it easily crystallizes when in contact with the air moisture. During the winter season MTHPA can solidify, but it can be easily remelted by simply heating.

Shelf life: 12 months from production date.

The information contained in this sheet is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of going to press. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing stated here may be taken or construed as implying of any existing patents. Nor is any warranty, whether explicit or implicit, given with regard to results to be obtained through the use of the aforesaid information.