

Technical data sheet

SMC 3300 RF R20

SMC 3300 RF R20 is a sheet moulding compound based on an unsaturated polyester resin, fire retardant grade, halogen-free, reinforced with glass fibres. This SMC has been developed for electrical application. **SMC 3300 RF R20** joint good mechanical properties and good fire protection grade.

SMC 3300 RF R20 is certified V0 3,0 mm by UL laboratories. **SMC 3300 RF R20** is formulated according to RoHS, REAC regulation (SVHC) and WEEE European legislation.

Material code ISO 11469 > UP-(MD+GF)65FR(60) <

UL FILE E 111031

Typical material properties

CHARACTERISTICS	METHOD	UNIT	VALUE
Quantity of glass	ISO 11667	%	20
Linear shrinkage	ISO 2577	%	0,15
Density	ISO 1183	g/cm ³	1,75
Water absorption	ISO 62 Met. 1	%	<u><</u> 0,2
Flexural strength	ISO 14125A	MPa	120
Flexural modulus	ISO 14125A	MPa	9.000
Impact strength (Charpy)	ISO 179	KJ/m ²	50
Rockwell hardness	ISO 2039-2	HRm	80
Heat distortion temperature HDT	ISO 75	°C	<u>></u> 200
Surface resistivity	IEC 93	Ω	10 ¹⁴
Volume resistivity	IEC 93	Ω mm	10 ¹⁴
Dielectric rigidity	IEC 243	KV/mm	18
Arc resistance	ASTM D 495	S	<u>></u> 180
Glow wire GWFI	IEC 695-2-1	°C	960
Flammability	UL 94	Class / mm	V0/3,0

Properties were determined on compression-moulded specimens according UNIPLAST rules project 412 and 413





Polynt S.p.A - Stab. Brembate di Sopra Via Caduti e Dispersi dell'Aeronautica,18 I-24030 Brembate di Sopra (Bg) Italy Tel. +39 035 623100 - Fax +39 035 333500



Storage and processing conditions

Storage at 15-25°C, in dry ambient and out of direct sun light

Moulding time 40 s/mm
Moulding pressure 70 - 110 bar
Moulding temperature 140 - 160°C

Note: The information contained in this sheet is correct and accurate and it based on our technical and scientific knowledge and on literature at the date of going to press. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing stated here may be taken or construed as implying of any existing patents. Nor is any warranty, whether explicit or implicit, given with regard to results to be obtained through the use of the aforesaid information.



