




Coating Resins Epoxies



Contents

Production Sites	3
Polynt Reichhold Group.....	3
Solvents – Abbreviations	4
Definitions.....	5
Trademarked Brands	5
Epoxies – Resins.....	6
Epoxies – Curing Agents	10
Glossary	12
Company Addresses	15

Production Sites



- Polynt Composites Canada, Inc.**
Brampton (ON) - Drummondville (QC)
- Polynt Composites USA Inc.**
Carpentersville (IL) - Chatham (VA) -
Ennis (TX) - Forest Park (GA) - Houston (TX)
- Marshall (TX) - North Kansas City (MO)
- Orlando (FL) - Sandusky (OH)

Polynt Group

After the merger on May 2017 the new Polynt Group is a global Company in the Intermediates, Coating and Composite Resins, Thermoset Compounds, Gel-coats and niche Specialties.

This combination enhances the Group’s leading position as a global vertically integrated specialty chemicals player, with significant global presence in Europe, North America and Asia, a strategy initiated by Polynt with the successful integration of PCCR and CCP in the last years and now further reinforced by Reichhold’s global scale, extensive product portfolio and R&D competencies.

Polynt Group is known for its superior quality and impressive range of products and with its excellent distribution network it can provide first-class service to customers whatever their market. Customer Service and Technical Service teams are renowned for their customer focus, offering the best service even after products have left manufacturing.

The Group strives to keep customers satisfied, assisting them in producing premium quality products every time they use its products.

Product innovation is important for the Group’s business and it’s the reason for which it constantly works with customers to find solutions to problems.

Introducing new or improved products ensures that Polynt Group continue not only to deliver what the market wants and needs, but also when it is wanted and needed.

Solvents – Abbreviations

A100, S	Aromatic 100
A150, R	Aromatic 150
DGBE, G5	Diethylene Glycol n-Butyl Ether
DMC	Dimethyl Carbonate
DPDME, G8	Dipropylene Glycol Dimethyl Ether
DPM	Dipropylene Glycol Monomethyl Ether
EEP, A7	Ethyl 3-Ethoxypropionate
EGBE, G4	Ethylene Glycol Monobutyl Ether, Butyl Cellosolve
EGPE, EP, G6	Ethylene Glycol Monopropyl Ether
EtOAc	Ethyl Acetate
EtOH, E	Ethyl Alcohol
G	Glycol and Glycol Ether
i-BuOH, B1	Isobutyl Alcohol
IBIB	Isobutyl Isobutyrate
IPA, D	Isopropyl Alcohol
Isopar G	Isoparaffin Solvent
LAMS, ML	Low Aromatic Mineral Spirits
MAK, K4	Methyl Amyl Ketone
MEK, K1	Methyl Ethyl Ketone
MIBK, K2	Methyl Isobutyl Ketone
MO	Odorless Mineral Spirits
MPK, K3	Methyl Propyl Ketone

MS, M	Mineral Spirits
n-BuAc, A4	n-Butyl Acetate
n-BuOH, B	n-Butyl Alcohol
n-PrOH	n-Propyl Alcohol
NMP, MP	n-Methyl-2-Pyrrolidone
PCBTF, E1	para-Chlorobenzotrifluoride (Oxsol® 100)
PGME, G3	Propylene Glycol Monomethyl Ether
PMA, A6	Propylene Glycol Monomethyl Ether Acetate
PnP, G2	Propoxy Propanol
s-BuOH, B2	Secondary Butyl Alcohol
t-BuAc, E2	t-Butyl Acetate
T	Toluene
TEA	Triethyleamine
DMEA	Dimethyl Ethanol Amine
NH3	Ammonia
TPM, T8	Tripropylene Glycol Monomethyl Ether
VM&P, V	VM&P Naphtha
VMS, E3	Volatile Methylsiloxane
W	Water
X	Xylene
Z	Mixed Solvents
6X3	Rule 66

Definitions

% NVM	Nonvolatile material expressed as a percent of the total weight of the resin solution.
% NVV	Nonvolatile material expressed as a percent of the total volume of the resin solution.
Eq. Wt.	Molecular weight divided by functionality, the latter being the number of a given reactive group present on an average molecule of the material. Expressed based on a solids basis.
pH	Degree of acidity or alkalinity of a solution expressed on a relative scale of 1 to 14 with 7 being neutral.
Particle Size	Average diameter of a distribution of particles, usually expressed in microns or nanometers.
Tg	Temperature at which the non-crystalline portion of a polymer is transformed from a viscous rubbery state to a brittle glass-like material. Generally an indication of the flexibility and hardness of a finished paint film.
MFFT	Minimum temperature at which an applied coating forms a continuous film, as evidenced by the visual lack of cracking or powdery appearance of film and film integrity, by testing the film on a temperature gradient plate.
Oil Type	Synthetic or naturally occurring vegetable material that contributes fatty acids used in producing alkyd resins.
Wt/Gal	Mass per volume of polymer as supplied expressed in pounds per gallon.
Viscosity	Measurement of a polymer's resistance to flow expressed in Gardner-Holdt units or centipoises.
Reduced Viscosity	Measured viscosity (as defined previously) at a specified percent weight solids typically lower than the solids of the polymer as supplied.
Color	Measurement of the light reflectance of a polymer in liquid form expressed in Gardner units on a relative scale of 1 to 14 with 1 being water white.
Acid Value (solids)	Number of milligrams of KOH required to neutralize the free acids in one gram of polymer solids.
OH Value	Hydroxyl value – number of milligrams of KOH equivalent to the hydroxyl groups available per gram of polymer. The hydroxyl equivalent weight is given by 56,100 divided by the hydroxyl value.
Solvents	Dilution solvents used to achieve the desired viscosity.

Trademarked Brands

ACRYLAMAC®, AROLON®	Solution Acrylics
ALCURE®	Polymeric Isocyanate Curatives
AQUAMAC®, AROLON®, SYNTHEMUL®	All Acrylic, Self-Crosslinking, Styrene Acrylic, and Vinyl Acrylic Latex
ARCHEMIS®	High Solids Long Oil Alkyds
AROFLINT®	Non-Isocyanate 2K Systems
BECKOSOL AQ®	Alkyd Emulsions
CARBAMAC®, UROTUF®	Oil Modified Urethanes, Uralkyds, Moisture Cure Urethanes, and Polyurethane Dispersions
CHEMACOIL®	Conventional Vinyl Oxazoline-Modified Esters
DURAMAC®, BECKOSOL®	Alkyds, Flat Alkyds, and Thixotropic Alkyds
DURAMAC®, KELSOL®	Water-Reducible Alkyds
HYDREAU®	Polyester Dispersions
MACOPOL®, AMBERLAC®	Copolymer Resins
POLYMAC®, FINE-CLAD®, FINE-TONE®	Powder Polyesters
POLYMAC®, AROPLAZ®	Liquid Polyesters
EPOTUF®	Epoxy Resins, Epoxy Curing Agents
REZIMAC®, EPOTUF®	Epoxy Esters
REZIMAC®, BECKOSOL®	Silicone-Modified and Phenolic-Modified Alkyds

Epoxies – Resins

PRODUCT	TYPE	% SOLIDS (WEIGHT)	DENSITY (LBS/GAL)	SOLVENTS	VISCOSITY (CPS @ 25° C)	GARDNER COLOR (MAXIMUM)
REACTIVE DILUENTS						
EPOTUF® 37-051	Aliphatic Polyfunctional	100	8.58	—	200 - 320	1
EPOTUF® 37-058	Aliphatic Monofunctional	100	7.47	—	20 max	1
SOLID RESIN						
EPOTUF® 37-002	Solid Bis-A Resin	100	9.90	—	250 - 340 @ 40% DEG	3
LIQUID RESIN						
EPOTUF® 37-138	Liquid Bis-F Resin	100	9.93	—	3000 - 4200	2
EPOTUF® 37-140	Liquid Bis-A Resin	100	9.70	—	10,500 - 13,500	1
EPOTUF® 91-836	Epoxy Novolac	75	9.13	MAK	330 - 1,000	3
WATER-BORNE LIQUID RESIN						
EPOTUF® 37-143	Liquid Bis-A Resin Dispersion	78	9.30	W	2,000 - 4,000	Milky
EPOTUF® 37-149	Type 7 Epoxy Dispersion	50	9.15	W / EGBD	1,000 - 3,000	Milky
DILUTED RESINS						
EPOTUF® 37-100	Aliphatic Polyfunctional	100	9.40	—	2,000 - 5,000	3
EPOTUF® 37-127	Aliphatic Monofunctional	100	9.20	—	500 - 800	1
EPOTUF® 37-128	Aromatic Monofunctional	100	9.30	—	500 - 1,000	2
EPOTUF® 37-130	Butyl Glycidyl Ether	100	9.45	—	500 - 700	2
SOLVENT-CUT RESINS						
EPOTUF® 38-501	Type 1	75	9.00	MIBK / X	4,630 - 14,800	3
EPOTUF® 38-502	Type 1	75	9.35	EEP	6,400 - 18,000	3
EPOTUF® 38-507	Type 1	75	9.10	T	4,630 - 14,800	3

EEW OR ACID (SOLID)	FEATURES AND BENEFITS
EEW = 665	High molecular weight aliphatic polyfunctional epoxy resin used as a modifier; improves adhesion; imparts flexibility and toughness; extends pot life; low viscosity
EEW = 295	Aliphatic monofunctional epoxy diluent based on Alkyl Glycidyl Ether C12-C14; low viscosity; low volatility and toxicity; allows high filler levels
EEW = 615	Solid glycidyl ether of Bisphenol A epoxy resin. Good chemical and corrosion resistance
EEW = 170	Undiluted liquid epoxy resin based on diglycidyl ether of Bisphenol-F (Bis-F); used alone or as a modifier for EPOTUF® 37-140; improves organic acid and solvent resistance; slows gel and thin film set times; greatly reduced crystallization potential
EEW = 185	Standard undiluted liquid epoxy resin based on Bisphenol-A (Bis-A); industry workhorse with good reactivity and resistance properties; high heat distortion temperature
EEW = 215	Modified epoxy Novolac; excellent corrosion and chemical resistance; highest heat distortion temperature
EEW = 200	Dispersion of liquid epoxy resin; can formulate compliant two component water-borne epoxy coatings when cured with EPOTUF® 37-680 and 37-685; freeze-thaw stable
HEW = 220	High performance protective coatings with melamine for bake or isocyanate for ambient cure. Good adhesion to steel and corrosion resistance
EEW = 220	100% reactive Bis-A epoxy based resin diluted 20% by weight with EPOTUF® 37-051; improves flexibility; extends pot life; good adhesion; medium viscosity
EEW = 200	100% reactive Bis-A epoxy based resin diluted 20% by weight with EPOTUF® 37-058; excellent toughness and flexibility; low color and viscosity
EEW = 200	100% reactive Bis-A epoxy based resin diluted 35% by weight with Phenol Glycidyl Ether C8-C10; excellent penetration; high filler loading; low viscosity
EEW = 185	100% reactive Bis-A epoxy based resin diluted 14% by weight with Butyl Glycidyl Ether; excellent flexibility; high filler loading; good penetration; low viscosity
EEW = 515	Solvent cut solid Bis-A epoxy resin; high molecular weight; fast dry; excellent toughness and impact resistance; good corrosion and chemical resistance
EEW = 465	Solvent cut solid Bis-A epoxy resin; high molecular weight; fast dry; excellent toughness and impact resistance; good corrosion and chemical resistance
EEW = 480	Solvent cut solid Bis-A epoxy resin; fast dry; good flexibility and impact resistance; good corrosion and chemical resistance

Epoxies – Resins

PRODUCT	TYPE	% SOLIDS (WEIGHT)	DENSITY (LBS/GAL)	SOLVENTS	VISCOSITY (CPS @ 25° C)	GARDNER COLOR (MAXIMUM)
MODIFIED RESINS						
EPOTUF® 37-151	Flexible	100	8.90	—	30,000 - 70,000	5
EPOTUF® 95-473	Urethane	60	8.60	MIBK / X / T / Cyclohexanone	550 - 1,290	3
EPOTUF® 98-411	Flexible	75	8.60	MEK	1,000 - 1,800	6
EPOTUF® G272-100	Elastomeric	100	8.97	—	500,000 - 900,000	14
EPOTUF® G293-100	CTBN	100	8.80	—	140,000 - 250,000	10
EPOTUF® G519-K2-70	CTBN	70	8.60	MIBK	4,000 - 10,000	9
SOLVENT-CUT EPOXY ESTERS						
EPOTUF® 38-406	Rosin Modified	60	7.70	MS	2,700 - 4,630	8
EPOTUF® 91-531	Epoxy Ester	55	8.10	X	1,500 - 2,700	6
EPOTUF® 91-853	Epoxy Ester	50	8.95	PCBTF / A100	1,000 - 2,600	10
REZIMAC® 12-1204	Epoxy Ester	60	7.75	MS	2,500 - 4,500	8
REZIMAC® 12-1222	Epoxy Ester	50	8.00	X	1,000 - 1,700	4
REZIMAC® 57-5839	Epoxy Ester	70	8.40	n-BuAc	1,300 - 2,300	8
WATER-REDUCIBLE EPOXY ESTERS						
EPOTUF® 38-690	Acrylic Modified	70	8.40	EGBE	14,800 - 38,800	7
EPOTUF® 38-692	Epoxy Ester	70	8.70	EGBE	9,000 - 15,000	8
EPOTUF® 38-699	Epoxy Ester	70	8.65	EGBE	9,000 - 15,500	8
EPOTUF® 91-263	Acrylic Modified	70	8.40	PnP	35,000 - 65,000	7
REZIMAC® 73-7331	Epoxy Ester	70	8.40	EGBE	12,500 - 18,000	8
WATER-DISPERSED EPOXY ESTERS						
EPOTUF® 38-694	Aqueous Dispersion	40	8.41	W / PnP / TEA	1,000 - 4,000	Milky
EPOTUF® 38-698	Acrylic Modified Aqueous Dispersion	42	8.50	W / PnP / TEA	500 max	Milky

EEW OR ACID (SOLID)	FEATURES AND BENEFITS
EEW = 500	Modifier for epoxies, 2K urethanes and baking polyester systems to improve flexibility, adhesion and weathering; very fast viscosity reduction curve; elongation up to 25%
EEW = 325	Urethane modified to provide improved adhesion, chemical and solvent resistance including aerospace hydraulic fluids
EEW = 485	Elastomer modified resin that produces flexible, impact resistant films when cured with conventional curing agents
EEW = 340	Elastomer modified resin designed as an additive or modifier to toughen epoxies, epoxy novolacs and PVC plastisols and to reduce brittleness
EEW = 340	Elastomer modified resin that produces flexible, impact resistant films when cured with conventional curing agents
EEW = 680	Elastomer modified resin that produces flexible, impact resistant films when cured with conventional curing agents
AV = 9 max	Good adhesion to steel; excellent toughness and abrasion resistance; good alkali resistance
AV = 6 max	Good hardness and abrasion resistance; good resistance to alkali, detergents, water and yellowing
AV - 8 max	Metal primers, rail car; reduced VOC due to exempt solvent content
AV = 10 max	Good hardness and adhesion; good abrasion and alkali resistance
AV = 3 max	Good chemical and corrosion resistance; good hardness and adhesion
AV = 3 max	HAPS-free; good corrosion and humidity resistance; very good gasoline resistance
AV = 54 - 60	Compatible with acrylic emulsions to improve corrosion resistance; fast air or force dry applications; excellent gloss, hardness and adhesion
AV = 45 - 49	Fast air or force dry primer applications; good corrosion resistance in thin films; good compatibility with inhibitive pigments
AV = 50 - 55	Fast air or force dry primer applications; good corrosion resistance in thin films; good compatibility with inhibitive pigments
AV = 52 - 62	HAPS-free; low VOC capability; excellent adhesion to a variety of substrates; fast air or force dry primers; good corrosion resistance
AV = 69 max	Fast dry; good corrosion and humidity resistance; good topcoat lifting resistance; adhesion to plastics
—	Pre-neutralized in HAPS-free solvents; low VOC capability; excellent hydrolytic stability; excellent corrosion resistance; excellent adhesion to wood, concrete and metal
—	Pre-neutralized in HAPS-free solvents; low VOC capability; bonds topcoat to concrete while increasing adhesion; good early water resistance

Epoxies – Curing Agents

PRODUCT	TYPE	% SOLIDS (WEIGHT)	DENSITY (LBS/GAL)	SOLVENTS	VISCOSITY (CPS @ 25° C)	GARDNER COLOR (MAXIMUM)
ALIPHATIC AMINES						
EPOTUF® 37-606	Adduct	100	8.15	—	200 - 400	5
EPOTUF® 37-611	Modified	100	8.05	—	5,500 - 8,500	3
EPOTUF® 37-614	Mannich Base	100	9.00	—	3,500 - 5,500	7
EPOTUF® 37-667	Modified	100	8.00	—	1,200 - 1,800	2
CYCLOALIPHATIC AMINES						
EPOTUF® 37-601	Adduct	100*	8.40	—	200 - 400	3
EPOTUF® 37-607	Adduct	100*	8.65	—	300 - 450	5
EPOTUF® 37-703	Modified	100*	8.60	—	40 - 100	1
WATER-BORNE POLYAMINE ADDUCTS						
EPOTUF® 37-680	Microgel Polyamine Adduct	42	8.90	W / EGPE	40 - 100	Milky
EPOTUF® 37-685	Microgel Polyamine Adduct	50	8.90	W / PGME	250 max	Milky
AMIDOAMINES						
EPOTUF® 37-620	Amide / Imidazoline	100	7.90	—	400 - 700	10
POLYAMIDES						
EPOTUF® 37-612	Amide / Imidazoline	100	7.90	—	10,500 - 19,000	10
EPOTUF® 37-618	Amide	70	7.70	X	884 - 2,290	12
EPOTUF® 37-621	Amide	60	7.49	IPA / T	1,000 - 2,800	11
EPOTUF® 37-625	Amide / Imidazoline	100	8.00	—	30,000 - 45,000	10
EPOTUF® 37-640	Imidazoline / Amide	100	8.30	—	9,000 - 15,000	10
EPOTUF® 37-650	Modified Amide / Imidazoline	100*	8.40	—	3,000 - 6,500	12

AHEW (SOLIDS)	AMINE VALUE (MG KOH/GM)	FEATURES AND BENEFITS
85	365	Moderate pot life; good gloss and blush resistant films; low viscosity
189	315	Fast cure; good moisture and blush resistance; improves resiliency and flexibility of other amines
50	760	Good cure speed at low temperature and/or high humidity; good chemical resistance; compatible with epoxy novolacs
157	267	Fast cure; good moisture and blush resistance; improves resiliency and flexibility of other amines; 1:1 mix ratio by volume with EPOTUF® 37-140
85	350	Based on isophorone diamine intended for room temp curing; excellent chemical resistance; good mechanical strength characteristics; light color; low viscosity
85	385	Good acid resistance and adhesion to damp concrete; can be blended with aliphatic amines to improve chemical and/or low temperature performance
93	320	Good color stability; high gloss and carbamation resistance under adverse conditions of high humidity and low temperature; very low viscosity
563	80	Long pot life and fast dry time when cured with EPOTUF® 37-143; low odor; good yellowing resistance; excellent elevated temperature and freeze/thaw stability
160	334	Excellent corrosion resistance on metal substrates when cured with EPOTUF® 37-143; low odor; <100 g/L VOC capability; high hardness; wide recoat window; good in-can coating stability
94	425	Good general purpose amidoamine; wide range of mix ratios; capable of high pigment loading; bonds well to damp concrete; resilient and impact resistant
130	340	High reactivity; low crystallization potential; low exudation; moderate viscosity
150	240	Provides flexibility, long pot life and good overall properties with solid epoxy resin; fast dry; suitable for a wide variety of substrates
500	90	High molecular weight; long pot life; excellent adhesion to steel and concrete; excellent water resistance; good impact resistance
120	350	Good balance of hardness and flexibility; excellent corrosion resistance; good adhesion and impact resistance; wide mix ratio; medium viscosity
100	385	High imidazoline content; lower viscosity and longer pot life than EPOTUF® 37-625
130	230	No induction time; performance similar to high molecular weight traditional polyamide/solid epoxy systems; low viscosity

* Reflects approximate weight % in cured film per Method 24 / ASTM D 2369

** C - Corrosive, NC - Non-Corrosive

*** For FDA applications, contact Polynt product regulatory group for specific use limitation information.

Glossary

Abrasion	Wearing away of a surface in service by action such as rubbing, scraping or erosion.
Abrasion Resistance	The ability of a coating to resist being worn away and to maintain its original appearance and structure when subjected to rubbing, scraping or erosion.
Acid Number or Value	The number of milligrams of KOH required to neutralize the free acids in 1 gram of polymer.
Aftertack	Film defect in which the coated surface, having once reached a tack-free stage, subsequently develops a sticky condition.
Anti-sintering	The property of reducing sintering.
Architectural Coatings	Coatings intended for on-site application to interior or exterior surfaces of residential, commercial, institutional or industrial buildings – as opposed to industrial coatings. Protective and decorative finishes applied at ambient temperatures.
Baking	The process of drying or curing a coating by the application of heat in excess of 65°C / 150°F. When below this temperature, the process is referred to as forced drying.
Block Resistance	Resistance to the undesirable sticking together of two painted surfaces when pressed together under normal conditions or under specified conditions of temperature, pressure, and relative humidity.
Blocked Isocyanate	An isocyanate material in which the isocyanate groups (NCO) are blocked from carrying out their normal chemical reactions by already having been reacted, either with a specific blocking agent or with themselves. In the latter case the blocked isocyanate is referred to as a uretdione type, because the NCO groups have linked themselves together to produce uretdione linkages. Common blocking agents are ε-caprolactam and triazole.
Blocking Agent	A chemical, such as ε-caprolactam, that reacts reversibly with isocyanate groups (NCO) such that at temperatures below the deblocking temperature it is covalently bonded to the NCO groups, thereby preventing these groups from reacting with anything else. At temperatures above the deblocking temperature, the blocking agent is released from the NCO groups thus allowing them to react with, for example, the hydroxyl groups of the surrounding polyester resin.
Blush, Blushing, “Bloom”	Film defect which appears as a milky opalescence as the film dries; can be a temporary or permanent condition. It is generally caused by rapid evaporation, moisture, or incompatibility.
Brush Drag	Resistance encountered when applying a coating by brush.
Brushability	The ability or ease with which a coating can be brushed.
Catalyst	An additive that speeds up a chemical reaction, such as curing, but takes no part in the reaction.
Chalk Resistance	The ability of a coating to resist the formation of a friable powder on the surface of its film caused by the disintegration of the binding medium due to degradative weather factors.
Chip Resistance	The ability of a coating or layers of coatings to resist total or partial removal, usually in small pieces, as a result of impact by hard objects or from wear during service.
Compatibility	Capacity of coatings from either different sources or of different compositions to be combined and applied so as to yield no visible or mechanically measurable differences in the cured film or application properties.
Conventional Solids	For the purposes of this reference guide, any material that is less than 70% solids. There may be exceptions.
Copolymer	A polymer consisting of molecules containing large numbers of units of two or more chemically different types in irregular sequence.
Corrosion Resistance	The ability of a substance to resist deterioration because of reaction with its environment.
Cracking	Generally, the splitting of a dry paint or varnish film, usually as a result of aging or flexing.
Crosslinking	Applied to polymer molecules, the setting up of chemical links between the molecular chains to form a three-dimensional or network polymer generally by covalent bonding. Crosslinking generally toughens and stiffens coatings. Thermosetting materials crosslink under the influence of heat and catalysis and, in some cases, electromagnetic radiation.
Cure	To change the properties of a polymeric system by chemical reaction into a final, more stable, usable condition by the use of heat, radiation or reaction with chemical additives.
D.O.I. (Distinctness of Image)	The sharpness with which image outlines are reflected by the surface of an object.
DCO	Dehydrated Castor Oil
Deblocking Temperature	The temperature at which the thermally reversible reaction between a blocking agent and an isocyanate group (NCO) begins to produce significant quantities of freed NCO groups available for reaction. The higher the temperature a blocked isocyanate is above its deblocking temperature, the more NCO groups are made available, and the faster crosslinking reactions can be. Conversely, when an isocyanate is below its deblocking temperature, no NCO groups are available for reaction.

Glossary

DFT	Dry film thickness
Dry	A film is considered dry when using moderate pressure, it feels firm to the touch.
Dry-Through	Film is considered dry-through when no distortion of the film (i.e., loosening, detachment, wrinkling, etc.) occurs when the thumb is borne downward while simultaneously turning the thumb through an angle of 90° in the plane of the film.
Dry-to-Touch	A film is considered dry-to-touch when it no longer adheres to the finger. The finger leaves no marks after touching the film, and film does not rub up appreciably when finger is lightly rubbed across the surface.
DTM (Direct-to-Metal)	Refers to coatings applied directly to an uncoated, non-primed metal substrate.
Edge Coverage	A powder coating’s ability to flow over, build and adhere to sharp corners, angles and edges.
Enamel	Topcoat that is characterized by its ability to form a smooth surface; originally associated with a high gloss but may also include lower degrees of gloss.
Equivalent Weight	The equivalent weight of a material is its molecular weight divided by its functionality, the latter being the number of a given reactive group present on an average molecule of the material. For polyester resins for coating powders, the resin equivalent weight is given by 56,100 divided by the resin acid value (for carboxyl polyesters) or 56,100 divided by the resin hydroxyl value (for hydroxyl polyesters). Expressed based on a solids basis.
Exempt Solvent	Any solvent that has not been declared photochemical reactive by any of several regulatory agencies.
Extruder	A device used to melt-mix plastics and/or powder coatings. An extruder utilizes heat and mechanical kneading to achieve a homogeneous mixture.
FDA	Food and Drug Administration
Flash Point	Lowest temperature of a liquid at which it gives off sufficient vapor to form an ignitable mixture with the air near the surface of the liquid or within the vessel used.
Glass Transition Temperature (Tg)	The temperature at which materials in general change from either a hard glassy state to a softer, rubbery state, or from a soft rubbery state to a harder glassy state.
HAP	Hazardous Air Pollutant
High Drink	A resin is said to be high drink when, as solvent is added, there is a slow viscosity reduction, enabling lower solids at a given viscosity.
High Solids	For the purposes of this reference guide, any material that is 70% solids or higher. There may be exceptions.
HDODA	Hexanediol diacrylate
HQMME	Hydroquinone monomethyl ether
Hybrid Powder Coating	A powder coating whose binder component is a blend of two different resins, such as polyester and epoxy. A “60/40” polyester/epoxy hybrid for example, would have a resin component comprising 60 wt/% polyester and 40 wt/% epoxy. The functional groups on each resin are balanced so as to fully react with each other at the given wt/% ratios of each resin.
Impact Fusion	The tendency for particles of powder coatings to agglomerate, fuse together, or build up on surfaces, because of mechanical impact during transportation within the powder application equipment.
Inhibitor	A negative catalyst which prevents or retards an undesirable chemical reaction.
Isocyanate	A material containing NCO groups that are available for reaction with a variety of other functional groups. Commonly those used in coating powders are polymeric in nature so as to increase their functionality.
Lacquer	Coating composition which is based on synthetic thermoplastic film-forming material dissolved in organic solvent that dries primarily by solvent evaporation.
Long Oil Alkyd	Alkyd resin containing more than 60% of oil in solids.
Medium Oil Alkyd	Alkyd of medium oil content, usually containing from 40-60% of oil in solids.
Melt Mixing	A predominant process for the manufacture of powder coatings involving the continuous compounding of the pigments, fillers, additives, resins and curing agents at elevated temperatures.
MFFT (Minimum Film Forming Temperature)	The minimum temperature at which an applied coating forms a continuous film, as evidenced by the visual lack of cracking or powdery appearance of film and film integrity, by testing the film on a temperature gradient plate.
Modified Alkyd	Modified alkyds are those in which the polybasic acid is substituted in part by a monobasic acid, of which the vegetable oil fatty acids are typical.
Oligomer	A polymer composed of molecules containing only two, three or a few repeating structural units.

Glossary

Particle Size	The average diameter of a distribution of particles, usually expressed in microns or nanometers.
PVC (Pigment Volume Concentration)	Ratio of the volume of pigment to the volume of total nonvolatile material (i.e., pigment and binder) present in a coating.
Pinholes	Film defect characterized by small pore-like flaws in a coating that extend entirely through the applied film and have the general appearance of pin pricks when viewed by reflective light.
Post Cure Embrittle-ment	A process whereby a cured coating exhibits increasing embrittlement and decreasing impact resistance with age.
Pot Life	The length of time a paint material is useful after its original package is opened or after catalyst or other ingredients are added.
Powder Coating	Finely divided particles of organic polymer that generally contain pigments, fillers and additives and which remain finely divided during storage under suitable conditions.
Precatalyzed	Usually refers to a resin that has a catalyst already added by the resin manufacturer. This ensures complete mixing of the catalyst with the resin and results in a resin that reacts faster than the uncatalyzed material.
Primer	The first complete coat of paint of a painting system applied to a surface.
Profile	Surface contour of a blast-cleaned or substrate surface, viewed from the edge.
Reactive Diluent	A viscosity reducer for coatings that has low volatility and will become a permanent part of the coating through chemical reaction.
Sagging	Downward moving of a paint film between the times of application and setting, resulting in an uneven coating having a thick lower edge.
Salt Spray Test	Test applied to metal finishes to determine their anticorrosive properties, involving spraying of common salt (sodium chloride) solution on the surface of a coated steel panel.
Shelf Life	The period of time for which a material can normally be stored and still be in a usable condition.
Short Oil Alkyd	Alkyd resin containing less than 40% oil in solids.
Sintering	The tendency of some powder coatings to agglomerate over time, often due to being stored too long at too high a temperature.
Skydrol® Resistance	Product is resistant to hydraulic fluid Skydrol.
Surface Dry	The premature drying of the surface of a liquid coating film so that the under portion is retarded in drying.
Syneresis	The separation of liquid from a gel.
Tack-Free	Freedom from tack of a coating after suitable drying time.
T-Bend Flexibility Test	Simple method for determining the flexibility of coatings by bending a coated metal test strip over itself. A panel is bent and pressed flat by means of a jig to achieve a 180° bend.
Telegraphing	Brush marks or other irregularities in the previous coat or substrate that show through the cured topcoat.
Tg	The temperature at which materials in general change from either a hard glassy state to a softer, rubbery state, or from a soft rubbery state to a harder glassy state.
TGIC (Triglycidyl Isocyanurate)	A curing agent for powder coating resins containing carboxyl groups.
TMA	Trimellitic anhydride
Two-Component Paint	A coating that is manufactured in two components that must be maintained separately until shortly before use.
Uretdione	A material containing uretdione linkages. These linkages are produced by two NCO groups reacting with each other. The original NCO groups are then no longer available for reaction and are termed "blocked." The reaction is reversible, such that the application of sufficient heat will cause the regeneration of the original NCO groups, which can then react. The advantage of this type of blocking is that there is no release of any blocking agent.
VOC (Volatile Organic Compound)	Any organic compound that participates in atmospheric photochemical reactions; that is, any organic compound other than those that the EPA designates as having negligible photochemical reactivity.
Weathering	Behavior of paint films when exposed to natural weather or accelerated weathering equipment, characterized by changes in color, texture, strength, chemical composition or other properties.
Yellowing	Development of a yellow color on aging.
Yellowing Resistance	The resistance a coating has to turning yellow due to, for example, extended cure times at high temperature, or the use of direct gas-fired curing ovens.

COMPANY ADDRESSES

AMERICAS

USA

Reichhold LLC 2
237 South Motor Avenue
Azusa, CA 91702
United States
Phone: +1 626 334 4974
Fax: +1 626 969 6978
email: contact.US@polynt.com

Polynt Composites USA Inc.
99 East Cottage Avenue
Carpentersville, IL 60110
United States
Phone: +1 800 322 8103
email: contact.US@polynt.com

Polynt Composites USA Inc.
920 Tightsqueeze Industrial Road
Chatham, VA 24531
United States
Phone: +1 434 432 8836
Fax: +1 434 432 1366
email: contact.US@polynt.com

Polynt Composites USA Inc.
201 Cedar Road
Ennis, TX 75119
United States
Phone: +1 972 875 8634
Fax: +1 919-990-7749
email: contact.US@polynt.com

Polynt Composites USA Inc.
71 Barnett Road
Forest Park, GA 30297
United States
Phone: +1 404 362 4000
email: contact.US@polynt.com

Reichhold LLC 2
54 Wamsley Road
Jacksonville, FL 32254
United States
Phone: +1 904 695 7500
Fax: +1 904 695 7517
email: contact.US@polynt.com

Polynt Composites USA Inc.
5851 FM 1998
Marshall, TX 75672
United States
Phone: +1 903 938 9571
Fax: +1 903 935 1801
email: contact.US@polynt.com

Reichhold LLC 2
6350 E Collins Rd
Morris, IL 60450
United States
Phone: +1 815 942 4600
Fax: +1 815 942 4722
email: contact.US@polynt.com

Polynt Composites USA Inc.
820 East 14th Avenue
North Kansas City, MO 64116
United States
Phone: +1 816 391 6000
Fax: +1 816 391 6337
email: contact.US@polynt.com

Polynt Composites USA Inc.
Regency Industrial Park
10124 Rocket Boulevard
Orlando, FL 32824
United States
Phone: +1 407 851 3030
Fax: +1 407 855 0674
email: contact.US@polynt.com

Reichhold LLC 2
425 South Pace Boulevard,
Pensacola, FL 32502
United States
Phone: +1 850 433 7621
Fax: +1 850 433 7699
email: contact.US@polynt.com

Polynt Composites USA Inc.
1321 First Street
Sandusky, OH 44870
United States
Phone: +1 419 625 1197
Fax: +1 419 625 8210
email: contact.US@polynt.com

Reichhold LLC 2
249 St. Louis Avenue
Valley Park, MO 63088
United States
Phone: +1 636 225 5226
Fax: +1 636 225 2954
email: contact.US@polynt.com

This brochure is intended to provide a comprehensive list of the products and services available from all business sectors in which are active the companies and/or corporations controlled, directly or indirectly, by Specialty Chemicals International Ltd (hereinafter referred to as «Polynt Group»). The information, recommendations, answers and/or opinions contained herein (which must be intended only for explanatory purposes) are aimed to assist customers on the basis of our technical and scientific knowledge as of today, taking into account that our products are intended for sale to industrial and commercial customers. However we require customers to inspect and test our products before use and to satisfy themselves as to contents and suitability for their applications: nothing herein shall constitute or shall be deemed to be any other warranty or a representation, express or implied, including merchantability or fitness for a particular purpose or results to be obtained from the use of such information, nor shall be taken or construed as infringing of any existing patents. Product names in capital letters are registered trademarks of the relevant member of Polynt Group. © Polynt S.p.A. - March 2025



Polynt Composites USA Inc.
99 East Cottage Avenue
Carpentersville, IL 60110
United States
Phone: +1 800 322 8103
email: contact.US@polynt.com
www.polynt.com

Polynt S.p.A.
Via Enrico Fermi, 51
24020 Scanzorosciate (BG)
Italy
Phone: +39 035 652 111
email: contact.IT@polynt.com
www.polynt.com

