

DISTITRON® 100 SV9

First Emission: 04/06/2007

Version: 04, 02/01/2017

Product type

Unsaturated polyester resin in styrene, DCPD

Appearance

Yellow - Dark - Transparent

Main resin characteristics

Low styrene content, Preaccelerated

Main applications

Mastics

Moulding informations

Mix with fillers and/or additives

Shelf life and storage

Store in the shade, out of direct sunlight. Keep storage temperature below 25°C. Unseal container just before use. Shelf-life will be reduced reaching higher temperature.

Precaution for handling

Read carefully the Safety Data Sheet

Note

FEATURES OF THE LIQUID RESIN

<i>Properties</i>	<i>Test Method</i>	<i>Unit</i>	<i>Typical values</i>
Specific weight at 20°C		g/cm ³	1,15
Brookfield viscosity at 25°C, sp 2 rpm 20	MT-CU025V	mPa.s	850 - 1050
Solid content	MT-CU001C	%	71 - 75
Reactivity	at 25°C + 3% PBO50		
Gel time	RS.08.G	min:sec	4:00 - 5:30
Delta	RS.08.G	min:sec	3:30 - 6:30
Exothermic peak	RS.08.G	°C	150 - 180
Shelf life at 23°C in the dark	MT-CU002S	months	3

PROPERTIES OF THE CURED UNREINFORCED RESIN

Curing cycle	24h at 23°C + 2h at 100°C + 1h at 100°C		
Tensile strength	ISO 527 (2012)	MPa	60
Tensile modulus	ISO 527 (2012)	MPa	2900
Elongation at break	ISO 527 (2012)	%	5,0
Flexural strength	ISO 178/B (2010)	MPa	135
Flexural modulus	ISO 178/B (2010)	MPa	2800
HDT	ISO 75 -2A (2013)	°C	55
Glass transition	ASTM E 1545 (2011)	°C	64
Barcol hardness at 25°C	ASTM D 2583 (2007)	units	35

The information contained in this document (which is to be intended only for explanatory purposes) is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of publication. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing in the information contained in this document shall be deemed to be a warranty or a representation (explicit or implicit) by the manufacturer, and/or taken or construed as infringing of any existing patents. The manufacturer shall not be under any liability or responsibility for any of the information provided under this document or for any errors, omissions or misstatements, even with regard to results to be obtained through the use of the aforesaid information.