

DISTITRON® 110 SXZ

First Emission: 20/05/2003

Version: 14, 02/01/2017

Product type

Unsaturated polyester resin in styrene, DCPD

Appearance

Bluish - Dark - Opalescent

Main resin characteristics

Low styrene emission, Low styrene content, Low exothermic peak, With catalyst indicator, Preaccelerated, Thixotropic

Main applications

Reinforced plastics, general purpose

Moulding informations

Hand lay up and Spray up

Shelf life and storage

Store in the shade, out of direct sunlight. Keep storage temperature below 25°C. Unseal container just before use. Shelf-life will be reduced reaching higher temperature.

Precaution for handling

Stir the resin before use, without use air bubbles, As the resin includes a film-forming agent, we recommend that the laminate should first rubbed down before bonding or relaminating., Read carefully the Safety Data Sheet

Note

FEATURES OF THE LIQUID RESIN

<i>Properties</i>	<i>Test Method</i>	<i>Unit</i>	<i>Typical values</i>
Specific weight at 20°C		g/cm ³	1,11
Brookfield viscosity at 25°C, sp 2 rpm 20	MT-CUT25V	mPa.s	450 - 630
Solid content	MT-CU001C	%	60 - 64
Reactivity	at 20°C + 2% MEKP50		
Gel time	RS.08.G	minutes	28 - 38
Delta	RS.08.G	minutes	16 - 25
Exothermic peak	RS.08.G	°C	150 - 180
Shelf life at 23°C in the dark	MT-CU002S	months	3

PROPERTIES OF THE CURED UNREINFORCED RESIN

Curing cycle	24h at 23°C + 2h at 100°C + 1h at 100°C		
Tensile strength	ISO 527 (2012)	MPa	45
Tensile modulus	ISO 527 (2012)	MPa	3300
Elongation at break	ISO 527 (2012)	%	1,5
Flexural strength	ISO 178/B (2010)	MPa	80
Flexural modulus	ISO 178/B (2010)	MPa	3300
HDT	ISO 75 -2A (2013)	°C	80
Barcol hardness at 25°C	ASTM D 2583 (2007)	units	40

The information contained in this document (which is to be intended only for explanatory purposes) is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of publication. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing in the information contained in this document shall be deemed to be a warranty or a representation (explicit or implicit) by the manufacturer, and/or taken or construed as infringing of any existing patents. The manufacturer shall not be under any liability or responsibility for any of the information provided under this document or for any errors, omissions or misstatements, even with regard to results to be obtained through the use of the aforesaid information.