Technical data sheet



DISTITRON® 514 CV2

Product type

Unsaturated polyester resin in styrene, Orthophthalic

Appearance

Neutral - Transparent

Main resin characteristics

Clear, unaccelerated

Main applications

Abrasives, chips

Moulding informations

Casting

First Emission: 23/05/2011

Version: 02, 02/01/2017

Shelf life and storage

Store in the shade, out of direct sunlight. Keep storage temperature below 25°C. Unseal container just before use. Shelf-life will be reduced reaching higher temperature.

Precaution for handling

Read carefully the Safety Data Sheet

Note

FEATURES OF THE LIQUID RESIN			
Properties	Test Method	Unit	Typical values
Specific weight at 20°C		g/cm³	1,11
Brookfield viscosity at 25°C, sp 2 rpm 20	MT-CU025V	mPa.s	180 - 250
Solid content	MT-CU001C	%	56 - 60
Reactivity	at 20°C + 0,9% Co 1% + 2% MEKP50		
Gel time	RS.08.G	minutes	7 - 9
Curing time	RS.08.G	min:sec	6:00 - 9:30
Exothermic peak	RS.08.G	°C	175 - 205
Shelf life at 23°C in the dark	MT-CU002S	months	3

PROPERTIES OF THE CURED UNREINFORCED RESIN					
Curing cycle	24h at 23°C + 2h at 100°C + 1h at 100°C				
Tensile strength	ISO 527 (2012)	MPa	70		
Tensile modulus	ISO 527 (2012)	MPa	4000		
Elongation at break	ISO 527 (2012)	%	2,0		
Flexural strength	ISO 178/B (2010)	MPa	140		
Flexural modulus	ISO 178/B (2010)	MPa	4000		
HDT	ISO 75 -2A (2013)	°C	70		
Glass transition	ASTM E 1545 (2011)	°C	80		
Barcol hardness at 25°C	ASTM D 2583 (2007)	units	45		

The information contained in this document (which is to be intended only for explanatory purposes) is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of publication. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing in the information contained in this document shall be deemed to be a warranty or a representation (explicit or implicit) by the manufacturer, and/or taken or construed as infringing of any existing patents. The manufacturer shall not be under any liability or responsibility for any of the information provided under this document or for any errors, omissions or misstatements, even with regard to results to be obtained through the use of the aforesaid information.