Technical data sheet



ENYDYNE® I 65133 A

Product type

Unsaturated polyester resin in styrene, DCPD

Appearance

Amber - Light - Transparent

Main resin characteristics

Preaccelerated, Medium reactivity, Low viscosity

Main applications

General purpose

HDT

Moulding informations

Injection moulding, RTM

First Emission: 26/10/2016

Version: 00, 24/11/2016

Shelf life and storage

Store in the shade, out of direct sunlight. Keep storage temperature below 25°C. Unseal container just before use. Shelflife will be reduced reaching higher temperature.

Precaution for handling

Read carefully the Safety Data Sheet

Note

FEATURES OF THE LIQUID RESIN			
Properties	Test Method	<i>Unit</i>	<i>Typical_values</i>
Specific weight at 20°C		g/cm³	1,10
Brookfield viscosity at 23°C, sp 1 rpm 50	MT-CU023V	mPa.s	120 - 160
Solid content	MT-CU001C	%	57 - 61
Reactivity	at 23°C + 1,2% Co 1% + 1,5% MEKP50		
Gel time	MT-CU151R	min:sec	5:30 - 7:30
23°C - Peak	MT-CU151R	minutes	14 - 20
Exothermic peak	MT-CU151R	°C	145 - 165
Shelf life at 23°C in the dark	MT-CU002S	months	6

PROPERTIES OF THE CURED UNREINFORCED RESIN 16 h at 40°C + 2 h at 90°C (+ 2 h at 120°C for HDT) **Curing cycle Tensile strength** ISO 527 (2012) MPa 38 ISO 527 (2012) MPa 3848 Tensile modulus ISO 527 (2012) % 1,19 **Elongation at break** MPa ISO 178 (2011) 62 Flexural strength ISO 178 (2011) MPa 3548 Flexural modulus °C

ISO 75 -2A (2013)

The information contained in this document (which is to be intended only for explanatory purposes) is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of publication. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing in the information contained in this document shall be deemed to be a warranty or a representation (explicit or implicit) by the manufacturer, and/or taken or construed as infringing of any existing patents. The manufacturer shall not be under any liability or responsibility for any of the information provided under this document or for any errors, omissions or misstatements, even with regard to results to be obtained through the use of the aforesaid information.

61