

NORSODYNE® FIREBLOCK H 81381 TFA

First Emission: 10/10/2016

Version: 02, 10/04/2017

Product type

Unsaturated Polyester Resin in styrene filled, without halogeneous component and antimony trioxide

Appearance

White

Main resin characteristics

Filled, Preaccelerated

Main applications

General purpose

Moulding informations

Hand lay up and Spray up

Shelf life and storage

Store in the shade, out of direct sunlight. Keep storage temperature below 25°C. Unseal container just before use. Shelf-life will be reduced reaching higher temperature.

Precaution for handling

Stir the resin before use, without use air bubbles, The final Fire resistance properties could change following the final structure of the piece and its use's condition. It will be necessary to verify the final properties on a prototype before industrial production.,
Read carefully the Safety Data Sheet

Note

FEATURES OF THE LIQUID RESIN

<i>Properties</i>	<i>Test Method</i>	<i>Unit</i>	<i>Typical values</i>
Specific weight at 20°C		g/cm ³	1,39
Brookfield viscosity at 23°C, sp 3 rpm 50	MT-CUT23V	mPa.s	700 - 900
Solid content	MT-CU001C	%	71 - 75
Reactivity	at 23°C + 1,5% MEKP50		
Gel time	MT-CU152R	minutes	25 - 31
23°C - Peak	MT-CU152R	minutes	45 - 55
Exothermic peak	MT-CU152R	°C	<45
Shelf life at 23°C in the dark	MT-CU002S	months	4

PROPERTIES OF THE CURED UNREINFORCED RESIN

Curing cycle	16 h at 80°C + 2 h at 140°C		
Tensile strength	ISO 527 (2012)	MPa	50
Tensile modulus	ISO 527 (2012)	MPa	2720
Elongation at break	ISO 527 (2012)	%	3
Flexural strength	ISO 178 (2011)	MPa	84
Flexural modulus	ISO 178 (2011)	MPa	2709
HDT	ISO 75 -2A (2013)	°C	97

The information contained in this document (which is to be intended only for explanatory purposes) is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of publication. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing in the information contained in this document shall be deemed to be a warranty or a representation (explicit or implicit) by the manufacturer, and/or taken or construed as infringing of any existing patents. The manufacturer shall not be under any liability or responsibility for any of the information provided under this document or for any errors, omissions or misstatements, even with regard to results to be obtained through the use of the aforesaid information.