

NORSODYNE® O 95905

First Emission: 13/10/2016

Version: 02, 11/04/2017

Product type

Unsaturated polyester resin, without styrene

Appearance

Yellow - Light - Transparent

Main resin characteristics

Monomers and solvents free

Main applications

Carrier resin for coloured and thickening pastes

Moulding informations

Shelf life and storage

Store in the shade, out of direct sunlight. Keep storage temperature below 25°C. Unseal container just before use. Shelf-life will be reduced reaching higher temperature.

Precaution for handling

Read carefully the Safety Data Sheet

Note

FEATURES OF THE LIQUID RESIN

<i>Properties</i>	<i>Test Method</i>	<i>Unit</i>	<i>Typical values</i>
Brookfield viscosity at 23°C, sp 3 rpm 50	MT-CU023V	mPa.s	1100 - 1300
Solid content	MT-CU001C	%	100
Shelf life at 23°C in the dark	MT-CU002S	months	9

PROPERTIES OF THE CURED UNREINFORCED RESIN

The information contained in this document (which is to be intended only for explanatory purposes) is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of publication. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing in the information contained in this document shall be deemed to be a warranty or a representation (explicit or implicit) by the manufacturer, and/or taken or construed as infringing of any existing patents. The manufacturer shall not be under any liability or responsibility for any of the information provided under this document or for any errors, omissions or misstatements, even with regard to results to be obtained through the use of the aforesaid information.