

Technical data sheet

Polimix® 100F

Version: June 2017

Chemical composition Polymeric plasticizer based on adipic acid and polyhydric alcohols

Specifications

Characteristics	Unit	Value	Test method	
Density at 25°C	g/ml	1.060 – 1.100	GM 012	ASTM D 4052-96
Refractive index n ²⁰ _D		1.460 – 1.465	GM 020	ASTM D 1045-95
Colour	Pt – Co	150 max.	PL02F	ASTM D 1045-95 ASTM D 1209-00
Acidity	mgKOH/g	2.0 max.	PL02C	ASTM D 1045-95
Viscosity at 25°C	mPa·s	700 - 1300	GM 022	ASTM D 445-96

Polimix® 100F is a pale yellow liquid, anhydrous with a low odour and free from matter in suspension. It is soluble with common organic solvents, practically insoluble in water and miscible and compatible with most of the monomeric plasticizers usually utilized to soften PVC (it is good laboratory practice to make a preliminary compatibility test in the specific PVC compound being considered).

The product **Polimix® 100F** due to its nature does not have a shelf life. However it can be stored in appropriate containers at a temperature of approximately 25 °C and the exclusion of humidity for at least 1 year, without losing its chemical properties.

Characteristics and applications

Polimix® 100F, being a low viscosity polymeric plasticizer, guarantees very good workability when it is employed to produce PVC compounds.

Permanence, low volatility, extraction resistance by oils, fats and hydrocarbons, low tendency to migrate are the main properties of the PVC articles produced with **Polimix® 100F**.

Polimix® 100F can be used alone or as a blend with monomeric plasticizers in a wide range of applications such as:

- electrical cables resistant to mineral oils;
- adhesive labels;
- electrical adhesive tapes;
- safety footwear resistant to fats and hydrocarbons;
- hydrocarbon resistant tubes;
- gloves and other protective garments;
- conveyor belts;
- leathercloth.

Technical Data Sheet

Polimix® 100F

Version: n°01 June/30/2017

First emission. January 2016

With reference to the Commission Regulation (EU) N° 10/2011 of 14 January 2011 on plastic materials and articles intended to come into contact with food, the **Polimix® 100F** is a polymeric substance, whose chemical composition satisfies the definition written in Annex I, table 1, column (4) of the Regulation (EU) N° 10/2011, REF N° 76866, FCM substance N° 73.

The above mentioned polymeric substance can be used as additive or aid to polymerisation with the following Group Restrictions (Annex I, Table 2):

31 (FCM: 73; 797). SML (T) 30 mg/Kg expressed as the sum of the substances

32 (FCM: 8; 72; 73; 138; 140; 157; 159; 207; 242; 283; 532; 670; 728; 729; 775; 783;797; 798; 810; 815). SML(T) 60 mg/Kg expressed as the sum of the substances.

Fat (Consumption) Reduction Factor (FRF) is applicable.

General properties in PVC compounds

The properties of **Polimix® 100F** were evaluated in comparison with those of **DIPLAST® NS (DINP; diisononylphthalate)** using the following formulation:

Formulation	PVC K70	Plasticizer	Ca/Zn	Stearic acid
(parts by weight) phr	100	50	1.2	0.3

The specimens were prepared by calendaring and moulding to obtain the thickness required for the different test methods.

Results

	Test method	Polimix® 100F	DIPLAST® NS
Shore "A" hardness	ISO 868	86	82
Cold flex °C (Clash & Berg)	ISO/R 458	-11.5	-26
Solution Temperature °C (*)	DIN 53408	148	129
Extraction resistance – % weight loss-(48 hours at 70°C)	ISO 175		
• Water		-0.52	-0.1
• Aqueous soap 1%		-3.2	- 0.7
• Olive oil		-4.62	-6.8
• Mineral oil		-3.91	-5.5
• n-Hexane (24hours at 23°C)		-1.19	-27.6
Volatility (7days at 100°C)	ISO 176	-2.2	-6.1
Rheological properties:			
• Dryblending time 83°C (°C) (Mixer P-600 : 100 RPM)	Brabender Plasticorder	3'52"	3'45"
• Gel time 88°C (°C) (Mixer W-50; 40 rpm 48g)	Brabender Plasticorder	11'30"	9'20"
• Fusion Temperature (°C) (Mixer W50, 5°C/min, 40rpm)	Brabender Plasticorder	123.3	117

(*) Solution temperature determined with dispersion of resin: two grams of PVC are placed in 48 grams of plasticizer and the solution is heated at 1°C/min.

Technical Data Sheet

Polimix® 100F

Version: n°01 June/30/2017

First emission. January 2016

Weight in loss 10 days at 40°C .in contact with food simulants

The properties of **Polimix® 100F** were evaluated using the following formulation:

Formulation	PVC K70	Plasticizer	Ca/Zn	Stearic acid
(parts by weight) phr	100	50	1.2	0.3

The specimens were prepared by calendaring and moulding to obtain the thickness required for the test methods (thickness 0,7mm ; surface area 0,5 dm²).

Results

Foods simulants	Weight in loss %
A: Ethanol 10% (water solution)	-0.49
D2: Olive oil	-5.5

The information contained here is correct and accurate and is based on our technical and scientific knowledge at the date of going to press.

Such information is, in all cases, relevant only with respect to the product as used in its pure state and only for the uses referred to in this publication.

Nothing stated here may be taken or construed as implying a breach of existing patents.

No warranty, either expressed or implicit, is given with regard to the results to be obtained from using this information.

Technical Data Sheet

Polimix® 100F

Version: n°01 June/30/2017

First emission. January 2016