



POLYCOR[®]

947 Series Special Flame Properties (SFP) Gel Coats

Copyright 1996-2016

Description

Gel coats in Polynt Composites' 947 Special Flame Properties (SFP) Series have been developed for the fiberglass industry where reduced burn characteristics are needed. When properly applied, 947 Series gel coats will meet UL 94V-0 requirements.

SFP gel coats are formulated with a **brominated** polyester resin system. Federal, state or local regulations may limit their use in certain applications. Check with the appropriate governing agency.

Since the flame properties of SFP gel coats in the cured state will vary depending on catalyzation, ultimate cure, and the laminating materials used, it is suggested that the user submit samples of the entire composite for testing by an independent lab.

Polynt's 947 Series gel coats are designed for interior, non-water immersion service **only**. Because these gel coats are formulated with a brominated polyester resin, they do not have good resistance to UV and/or water attack.

These gel coats are ready to use, easy to spray, sag resistant, fast curing and require only the addition of the proper amount of an appropriate methyl ethyl ketone peroxide to cure.

SFP's are available in many visually appealing colors. Certain custom color matching is available on request.

Typical Properties (77°F)

These values shown below may or may not be manufacturing control criteria. They are listed as a reference guide only. Particular batches may not conform exactly to the numbers listed because storage conditions, temperature changes, age, and testing equipment (type and procedure) can each have a significant effect on the test results. Gel coats with properties outside of these ranges may perform acceptably.

Test	POLYCOR [®] 947 Series
Viscosity ⁽¹⁾	
White and Off-Whites	15,500-20,500 cps
Various Colors	10,000-18,000 cps
Thixotropic Index (2/20)	7.0
Flash Point	85°F
% VOC	39%
Weight per Gallon (lbs/gallon)	10.0-12.5 depending on color
Gel Time @t 1.8% MEKP ⁽²⁾	12 minutes
Lay-up Time	45-60 minutes
Sag Resistance	Good @ 20 mils
Hide (most formulations)	Complete @ 10 mils

⁽¹⁾ Brookfield RVF #4 Spindle @ 4 rpm

⁽²⁾ Arkema Luperox[®] DDM-9



Reds, yellows and dark blues may have low hiding power. Ask a Polynt representative whether the selected red, yellow or blue colors require special application procedures. Some difference may include increased film thickness in multiple cured applications.

Application

Do not overmix POLYCOR® 947 gel coats. Overmixing breaks down gel coat viscosity, increasing tendencies to sag, and causes styrene loss, which could contribute to porosity. Gel coats should be mixed once per day for 10 minutes. The gel coat should be mixing to the sides and bottom of the container with the least amount of turbulence possible. Air bubbling should not be used for mixing. It is not effective, and serves as a potential for water or oil contamination.

SFP gel coats are generally formulated for both airless and conventional spray application. Brushing or rolling is not recommended. Refer to PB-16 (Application Guide) and PB-3 (Equipment Selection) Bulletins for additional, specific recommendations.

Polynt Composites recommends a gel coat delivery rate of no more than 2.5 pounds per minute with conventional air-atomized equipment, and no more than 4 pounds per minute with airless equipment.

For optimum results, uniform catalyst mix must be achieved. Even with the equipment properly calibrated, potential problems can occur due to: poorly atomized catalyst; surging problems (gel coat or catalyst); poor tip alignment (catalyst to gel coat mix); contamination; and poor application procedures, which will quickly negate all benefits of calibration. The equipment and application procedures must be monitored on a routine basis to ensure proper application and cure of the gel coat. Adhere to all equipment manufacturers' recommendations.

Avoid overspray settling on mold surfaces by starting the spray pattern closest to the vapor/air exhaust and progressing to the opposite mold end. Maintain recommended spray distances from the mold surface. Closer spray distances or larger tips may be required in hot weather to avoid dry spray buildup.

For best overall performance properties, a wet film thickness of 18 ± 2 mils is recommended as ideal. Films less than 12 mils may not cure properly, may be hard to patch, have more print-through, and are more susceptible to water blisters. Films above 24 mils may pre-release, trap porosity, crack and are more subject to weathering discoloration.

Proper mold maintenance is important. Although POLYCOR® 947 gel coats have excellent patching properties, minimal repair work is always desirable. Sanding and compounding can hasten the chalking and loss of gloss of all gel coats.

Cure

It is recommended that gel time be checked in the customer's plant because age, temperature, humidity and catalyst will produce varied gel times. All data referencing gel or cure refers specifically to Arkema Luperox® DDM-9 catalyst. United Initiators Norox® MEKP-9, Norox® MEKP-9H, Akzo Nobel CADOX L-50a and CADOX D-50 are expected to yield similar performance. Arkema Luperox® DHD-9, United Initiators Norox® MEKP-925 and Norox® MEKP-925H, and Pergan HP-90 may yield slightly shorter gel and cure times.

The catalyst level should not exceed 3% or fall below 1.2% for proper cure. Recommended range is 1.2% to 3.0% with 1.8% at 77°F being ideal. Normally, the gel coat film is ready for lamination in 45 to 60 minutes. This time element is dependent on material temperature, room temperature, humidity, air movement, and catalyst concentration. Special fast-cure versions are available but must be requested.



These products offer lay-up times of 30 minutes or less depending on gel times. Fast cure products have shorter stability and should not be inventoried over 45 days.

These products (standard or fast cure) should not be used when temperature conditions are below 60°F, as curing may be adversely affected.

Caution

Gel coats in the POLYCOR® 947 Series are not compatible in the liquid state with ISO/NPG gel coats or ISO/NPG resins. Spray and pumping equipment must be completely clean of these gel coats or resins before POLYCOR® 947 gel coat can be used

Do not add any material, other than the recommended methyl ethyl ketone peroxide, to this product without the advice of a Polynt Composites representative.

Storage Limitations

Uncatalyzed, standard cure gel coats have a shelf life of 120 days from date of manufacture when stored at 73°F or below, in a closed, factory-sealed, opaque container, and out of direct sunlight. Fast cure gel coats (gel time less than 9.0 minutes) are stable for 60 days. Shelf life is cut in half for every 20°F over 73°F. Totes of product can have even shorter shelf life – 66% of that for drums.

SDS / Data Sheets

SDS and data sheets can be obtained by contacting your Polynt representative or Polynt Customer Service at 800-322-8103.

POLYNT SAFETY INFORMATION

All sales of products manufactured by Polynt Composites USA Inc. and described herein, are made solely on condition that Polynt Composites USA customers comply with applicable health and safety laws, regulations and orders relating to the handling of our products in the workplace. Before using, read the following information, and both the product label and Safety Data Sheet pertaining to each product.

Most products contain styrene. Styrene can cause eye, skin and respiratory tract irritation. Avoid contact with eyes, skin and clothing. Impermeable gloves, safety eyewear and protective clothing should be worn during use to avoid skin and eye contact. Wash thoroughly after use.

Styrene is a solvent and may be harmful if inhaled. Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Extended exposure to styrene at concentrations above the recommended exposure limits may cause central nervous system depression causing dizziness, headaches or nausea and, if overexposure is continued indefinitely, loss of consciousness, liver and kidney damage.

Do not ingest or breathe vapor, spray mists or dusts caused by applying, sanding, grinding and sawing products. Wear an appropriate NIOSH/MSHA approved and properly fitted respirator during application and use of these products until vapors, mists and dusts are exhausted, unless air monitoring demonstrates vapors, mists and dusts are below applicable exposure limits. Follow respirator manufacturer's directions for respirator use.

The 12th Report on Carcinogens issued by the National Toxicology Program lists styrene as a "reasonably anticipated" carcinogen, but the Report cautions that the NTP listing does not mean that styrene presents a risk to persons in their daily lives. The Styrene Information and Research Center does not agree with the classification as it did not include a review of all available data. SIRC states: "HHS included styrene in the 12th RoC despite the fact that European Union regulators have determined styrene does not represent a human cancer concern. E.U. scientists reviewed the full styrene database, weighing all of the available data in reaching their conclusion."

The International Agency for Research on Cancer (IARC) reclassified styrene as Group 2B, "possibly carcinogenic to humans." This revised classification was not based on new health data relating to either humans or animals, but on a change in the IARC classification system. The Styrene Information and Research Center does not agree with the reclassification and published the following statement: Recently published studies tracing 50,000 workers exposed to high occupational levels of styrene over a period of 45 years showed no association between styrene and cancer, no increase in cancer among styrene workers (as opposed to the average among all workers), and no increase in mortality related to styrene.

Styrene is classified by OSHA and the Department of Transportation as a flammable liquid. Flammable products should be kept away from heat, sparks, and flame. Lighting and other electrical systems in the workplace should be vapor-proof and protected from breakage.

Vapors from styrene may cause flash fire. Styrene vapors are heavier than air and may concentrate in the lower levels of molds and the work area. General clean air dilution or local exhaust ventilation should be provided in volume and pattern to keep vapors well below the lower explosion limit and all air contaminants (vapor, mists and dusts) below the current permissible exposure limits in the mixing, application, curing and repair areas.

Some products may contain additional hazardous ingredients. To determine the hazardous ingredients present, their applicable exposure limits and other safety information, read the Safety Data Sheet for each product (identified by product number) before using. If unavailable, these can be obtained, free of charge, from your Polynt Composites representative or from: Polynt Composites USA Inc., 99 East Cottage Avenue, Carpentersville, IL 60110, 800-322-8103.

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water. If affected by inhalation of vapors or spray mist, remove to fresh air. If swallowed, get medical attention.

Those products have at least two components that must be mixed before use. Any mixture of components will have hazards of all components. Before opening the packages read all warning labels. Observe all precautions.

Keep containers closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with applicable regulations. Emptied containers may retain hazardous residue. Do not cut, puncture or weld on or near these containers. Follow container label warnings until containers are thoroughly cleaned or destroyed.

FOR INDUSTRIAL USE AND PROFESSIONAL APPLICATION ONLY. KEEP OUT OF REACH OF CHILDREN.

LIMITED WARRANTY AND LIMITATION OF LIABILITY

LIMITED WARRANTY.

Seller warrants that: (i) Buyer shall obtain good title to the product sold hereunder, (ii) at shipment such product shall conform to Seller's specifications for the product; and (iii) the sale or use of such product will not infringe the claims of any U.S. patent covering the product itself, but Seller does not warrant against infringement which might arise by the use of said product in any combination with other products or arising in the operation of any process. **SELLER MAKES NO OTHER WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE, EVEN IF THAT PURPOSE IS KNOWN TO SELLER. ANY ADDITIONAL REPRESENTATIONS OR SUGGESTIONS REGARDING THE PRODUCT OR ITS POSSIBLE USES ARE BASED UPON SELLER'S GOOD FAITH OPINION AND BELIEF, BUT ARE NOT TO BE CONSTRUED AS AFFIRMATIONS OF FACT, PROMISES, OR DESCRIPTIONS, AND SHALL IN NO WAY BE DEEMED PART OF THE SALE OF PRODUCT.** In particular, and without limiting the foregoing, because of environmental and use conditions beyond Seller's control, Seller offers no warranty and makes no promise concerning the results that may be obtained by the Buyer (or the Buyer's customer) with the product or the performance of the product. Each user should satisfy itself, by adequate testing, of the suitability of the product for its particular application.

LIMITATION OF LIABILITY.

- (a) Seller's total liability for any claim arising out of or in connection with this contract, including for breach of contract, warranty, statutory duty, or for other tort, including seller's negligence, shall not exceed the purchase price of such product as to which such liability arises. Seller shall not be liable for any injury, loss or damage, resulting from the handling or use of the product shipped hereunder whether in the manufacturing process or otherwise. **IN NO EVENT SHALL SELLER BE LIABLE FOR SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES, INCLUDING WITHOUT LIMITATION LOSS OF PROFITS, CAPITAL OR BUSINESS OPPORTUNITY, DOWNTIME COSTS, OR CLAIMS OF CUSTOMERS OR EMPLOYEES OF BUYER, WHETHER IN AN ACTION UNDER CONTRACT, NEGLIGENCE OR ANY OTHER THEORY, ARISING OUT OF OR IN CONNECTION WITH THIS CONTRACT, OR THE USE, INABILITY TO USE, OR PERFORMANCE OF THE PRODUCT.**
- (b) If Seller furnishes technical or other advice to Buyer, whether or not at Buyer's request, with respect to processing, further manufacture, other use or resale of the products, Seller shall not be liable for, and Buyer assumes all risk of, such advice and the results thereof.

The information provided is believed to be accurate at the time of preparation, or prepared from sources believed to be reliable, but it is the responsibility of user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use.