Polynt S.p.A - Stab. Brembate di Sopra Via Caduti e Dispersi dell'Aeronautica,18 I-24030 Brembate di Sopra (Bg) Italy Tel. +39 035 623100 - Fax +39 035 333500



# Technical data sheet

## **SMC 4200 R23**

**SMC 4200 R23** is a sheet moulding compound based on an unsaturated polyester resin reinforced with glass fibres. This SMC has been developed for sink and tray application. **SMC 4200 R23** joints good mechanical properties with stain and chemical resistance. **SMC 4200 R23** has been studied to show a uniform pigmentation on the part moulded. **SMC 4200 R23** is formulated according to RoHS, REAC regulation (SVHC) and WEEE European legislation.

### Material code ISO 11469 > UP-(MD+GF)65<

#### **Typical material properties**

CHARACTERISTICS	METHOD	UNIT	VALUE
Quantity of glass	ISO 11667	%	23
Linear shrinkage	ISO 2577	%	0,1
Density	ISO 1183	g/cm <sup>3</sup>	1,7
Water absorption	ISO 62 Met. 1	%	≤ 0,2
Flexural strength	ISO 14125A	MPa	130
Flexural modulus	ISO 14125A	MPa	9.500
Impact strength (Charpy)	ISO 179	KJ/m <sup>2</sup>	50
Heat distortion temperature HDT	ISO 75	°C	> 200
Rockwell hardness ( M scale )	ISO 2039-2	HRm	80

Properties were determined on compression-moulded specimens according UNIPLAST rules project 412 and 413

#### Storage and processing conditions

Storage in a dry place at 15-25°C, out of direct sunlight

Moulding time 40 s/mm
Moulding pressure 70 - 110 bar
Moulding temperature 140 - 160°C

Note: The information contained in this sheet is correct and accurate and it based on our technical and scientific knowledge and on literature at the date of going to press. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing stated here may be taken or construed as implying of any existing patents. Nor is any warranty, whether explicit or implicit, given with regard to results to be obtained through the use of the aforesaid information.





