

## Technical data sheet

### SMC 4400 R12

**SMC 4400 R12** is a sheet moulding compound based on an unsaturated polyester resin reinforced with glass fibres. This SMC has been developed for co-moulding with wood panel. **SMC 4400 R12** joint excellent appearances and low tendency to absorb liquid or dust. **SMC 4400 R12** is formulated according to RoHS, REAC regulation (SVHC) and WEEE European legislation.

**Material code ISO 11469 >UP-(MD+GF)60<**

#### Typical material properties

CHARACTERISTICS	METHOD	UNIT	VALUE
Quantity of glass	ISO 11667	%	12
Linear shrinkage	ISO 2577	%	0,15
Density	ISO 1183	g/cm <sup>3</sup>	1,7
Water absorption	ISO 62 Met. 1	%	≤ 0,2
Flexural strength	ISO 14125A	MPa	90
Flexural modulus	ISO 14125A	MPa	9.500
Impact strength (Charpy)	ISO 179	KJ/m <sup>2</sup>	40
Rockwell Hardness Scale M	ISO 2039-2	HRM	80
Heat distortion temperature HDT	ISO 75	°C	> 200

Properties were determined on compression-moulded specimens according UNIPLAST rules project 412 and 413

#### Storage and processing conditions

Storage	in a dry place at 15-25°C, out of direct sunlight
Moulding time	40 s/mm
Moulding pressure	50 - 110 bar
Moulding temperature	140 - 150°C

Note: The information contained in this sheet is correct and accurate and it based on our technical and scientific knowledge and on literature at the date of going to press. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing stated here may be taken or construed as implying of any existing patents. Nor is any warranty, whether explicit or implicit, given with regard to results to be obtained through the use of the aforesaid information.

