

## Technical data sheet

# Trimellitic anhydride (TMA)

Version: February 2007


### Synonyms

1,3-Dihydro-1,3-dioxoisobenzofuran-5-carboxylic acid; 4-Carboxyphthalic anhydride; CPA; Trimellitic acid anhydride; 1,3-Dioxo-1,3-dihydro-2-benzofuran-5-carboxylic acid.

### Formula

$C_9H_4O_5$

### Structural formula



**Molecular weight:** 192.1

### CAS number

552-30-7

### EINECS number

209-008-0

### Product specification

Characteristics	Unit	Value	Method*	Reference
Purity (anhydride content)	%	97.5 min	TMA 02	
DE		1.3 max	TMA 03	
Solidification point	°C	166 min	GM013	ASTM D-1493
Colour in molten state	Hz	150 max	GM011	ASTM D-3366
Phthalic acid content	%	0.1 max	GM001	

\* Internal methods available upon request.

## Typical properties

Characteristics	Unit	Value
Boiling point	°C	390
Density @ 200°C (molten)	g/ml	1.332 g/ml
Vapour pressure @ 200 °C	mmHg	2.0
Viscosity @ 200°C	mPa.s	9.1

## Main applications

TMA is mainly used as intermediate for plasticizers for PVC (Trimellitates), polyester powder coatings, polyester-imide resins, polyamide-imides and in water-soluble alkyd resins.

## Handling

Packaging: paper bag 25 kg;  
big bags 500/1000 kg  
bulk, in autosilos.

Storage: it must be stored for a limited time only, away from open flames and other potential ignition sources, in cool, dry, well-ventilated place and protected from light and moisture.

Shelf life: 12 months from production date.

*The information contained in this sheet is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of going to press. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing stated here may be taken or construed as implying of any existing patents. Nor is any warranty, whether explicit or implicit, given with regard to results to be obtained through the use of the aforesaid information.*